

# STELLITE® 12 ALLOY

## TECHNICAL DATA

TIG & OXY-ACETYLENE WELDING

MMA WELD DEPOSITION

MIG WELD DEPOSITION

PTA & LASER WELD DEPOSITION

FROF & PLASMA SPRAY DEPOSI-

### Nominal Composition (mass %) and Physical Properties

Co	Cr	W	C	Others	Hardness	Density	Melting Range
Base	27-32	7.5-9.5	1.4-1.7 (hardfacing) 1.7-2.0 (casting)	Ni, Fe, Si, Mn	45-51 HRC 435-590 HV	8.53 g/cm <sup>3</sup> 0.308 lb/in <sup>3</sup>	2192-2489 °F 1200-1365 °C

**Stellite® cobalt base alloys** consist of complex carbides in an alloy matrix. They are resistant to wear, galling and corrosion and retain these properties at high temperatures. Their exceptional wear resistance is due mainly to the unique inherent characteristics of the hard carbide phase dispersed in a CoCr alloy matrix.

**Stellite® 12** could be considered an intermediate alloy between **Stellite® 6** and **Stellite® 1**. It contains a higher fraction of hard, brittle carbides than **Stellite® 6**, and has increased resistance to low-angle erosion, abrasion, and severe sliding wear whilst retaining reasonable impact and cavitation resistance. **Stellite® 12** is often used self-mated or running against **Stellite® 6** or **Stellite® 1**. The higher tungsten content provides better high-temperature properties compared to **Stellite® 6**, and it can be used at temperatures up to about 700 °C.



Optical Micrograph of a Stellite® 12 PTA Deposit at 500X.

**Stellite® 12** is typically used for cutting tools that need to withstand abrasion, heat and corrosion. Examples include industrial knives for cutting carpets, plastics, paper and synthetic fibres; and saw tips in the timber industry. It is also used for control plates in the beverage industry, pump vanes, bearing bushes and narrow-neck glass mold plungers; and for hardfacing of engine valves, pinch rollers in the metal-processing industries, and rotor blade edges.

### Corrosion Resistance

The typical electrode potential in sea water at room temperature is approximately -0.3 V (SCE). Like stainless steels, **Stellite® 12** corrodes primarily by a pitting mechanism and not by general mass loss in seawater and chloride solutions. Information regarding corrosion resistance in other corrosive environments can be provided on request.

### Nominal Thermal Expansion Coefficient (from 20°C to stated temperature)

	100°C (212°F)	200°C (392°F)	300°C (572°F)	400°C (752°F)	500°C (932°F)	600°C (1112°F)	700°C (1292°F)	800°C (1472°F)	900°C (1652°F)	1000°C (1832°F)
µm/m.K	11.5	12.1	12.6	12.9	13.3	13.8	14.3	14.8	15.2	15.6
µ-inch/inch-°F	6.4	6.7	7.0	7.2	7.4	7.7	7.95	8.2	8.45	8.7

### Nominal Tensile Properties at Room Temperature

	Ultimate Tensile Strength Rm		Yield Stress Rp(0.2%)		Elongation	Elastic Modulus	
	ksi	MPa	ksi	MPa	A(%)	psi	GPa
Castings	107	740	84	580	<1	32.8x10 <sup>6</sup>	226
Stellite® HS-12 (*)	174	1200	130	900	2	30.1x10 <sup>6</sup>	208

(\*) "HS" = HIP -consolidated from the powder form.

### Nominal Hot Hardness (DPH) as-cast

20°C (68°F)	100°C (212°F)	200°C (392°F)	300°C (572°F)	400°C (752°F)	500°C (932°F)	600°C (1112°F)	700°C (1292°F)	800°C (1472°F)	900°C (1652°F)
546	456	418	390	380	371	362	328	232	153

### Thermal and Electrical Properties

	Approximate value at Room Temperature	
Thermal conductivity	14.6 W/m.K	100 Btu-in/hr/ft <sup>2</sup> /°F
Electrical resistivity	98 µ-ohm.cm	38.6 µ-ohm.inch

### Product Forms and Cross Reference Specifications

Stellite® 12 is available as welding wire, rod, powder, and electrodes; finished castings and P/M parts. Deloro Stellite also offers hardfacing services. Stellite® 12 can be supplied to the following specifications:

SPECIFICATION	PRODUCT FORM	SPECIFICATION	PRODUCT FORM
UNS R30012	Rod, Castings	AWS A5.21 / ASME BPVC IIC SF A 5.21 ERCoGB	Rod
UNS W73012	Electrode	AWS A5.21 / ASME BPVC IIC SF A 5.21 ERCCoGB	Wire
UNS W73042	Wire	AWS A5.13 / ASME BPVC IIC SF A 5.13 ECoGB	Electrode

Stellite is a registered Trade Name of Deloro Stellite.

Deloro Stellite manufactures sophisticated alloys in the form of castings, powders, coatings, consumables, and machined parts that resist wear, corrosion, and abrasion. Information provided in this document is intended only for general guidance about Deloro Stellite products and is the best information in our possession at the time. Product users may request information about their individual use of our products, but Deloro Stellite does not warrant or guarantee this information in any way. Selection and purchase of Deloro Stellite products is the sole responsibility of the product user based on the suitability of each use. Individual applications must be fully evaluated by the user, including compliance with applicable laws, regulations, and non-infringement. Deloro Stellite cannot know or anticipate the many variables that affect individual product use and individual performance results may vary. For these reasons, Deloro Stellite does not warrant or guarantee advice or information in this document, assumes no liability regarding the same, and expressly disclaims any warranty of any kind, including any warranty of fitness for a particular purpose, regarding the same.



UK SALES OFFICE  
 Deloro Stellite  
 Cheney Manor Industrial Estate  
 Swindon SN2 2PW  
 UK  
 Tel: (+44) 1793-498500  
 Fax: (+44) 1793-498501  
 E-Mail: saleshad@stellite.com  
 Literature Number: 461-12  
 Copyright © 2007 Deloro Stellite  
 Printed in USA  
 www.stellite.com

US SALES OFFICE  
 Stellite Coatings  
 1201 Eisenhower Drive North  
 Goshen, Indiana 46526  
 USA  
 Tel: (+1) 574-534-2585  
 Fax: (+1) 574-534-3417  
 E-Mail: saleshad@stellite.com